

Nomex® Xtreme Arc

Fabric protection performance

Property	Standard	Units/description	Nomex® Xtreme Arc	Nomex® Xtreme Arc
Fabric construction	—	—	Double-face weave	Double-face knit
Basis weight	—	oz/yd ² (g/m ²)	6.5 (220)	6.9 (234)
Arc Rating (Arc Thermal Performance Value [ATPV])	ASTM F1959 IEC 61482-1-1	cal/cm ²	>12 (16-19)	>12 (14-17)
Energy Breakopen Threshold (EBT)	ASTM F1959 IEC 61482-1-1	cal/cm ²	—	>12 (17)
Thermal manikin	NFPA 2112	TPBI (%)	9	9
Box test	IEC 61482-1-2	Rating	Class 1	—

Typical physical properties (ASTM, NFPA)

Property	Standard	Units/description	Nomex® Xtreme Arc	Nomex® Xtreme Arc
Fabric construction	—	—	Double-face weave	Double-face knit
Basis weight	ASTM D3776	oz/yd ²	6.5	6.9
Tensile strength (Grab test)	ASTM D5034	Warp (lbf) Weft (lbf)	310 260	— —
Elmendorf tear	ASTM D1424	Warp (lbf) Weft (lbf)	28 27	— —
Burst strength	ASTM D3786	PSI	—	180
Heat transfer performance (HTP)	NFPA 2112 Section 8.2	Spaced (cal/cm ²) Contact (cal/cm ²)	18 13	17 14
Shrinkage after 5 home laundering cycles	AATCC 135	Machine (%) Cross (%)	<3 <3	— —

Typical physical properties (ISO, EN)

Property	Standard	Units/description	Nomex® Xtreme Arc	Nomex® Xtreme Arc
Fabric construction	—	—	Double-face weave	Double-face knit
Basis weight	ISO 3801	g/m ²	220	234
Tensile strength	ISO 13934-1	Warp (N) Weft (N)	1411 1232	— —
Tear strength	ISO 13937-2	Warp (N) Weft (N)	57 62	— —
Burst strength	ISO 13938-2	kPa	—	982
Dimensional stability	ISO 5077	Machine (%) Cross (%)	<3 <3	<5 <5

◀ DUPONT ▶

Nomex®

For more information on Nomex® Xtreme Arc including pilling, colorfastness, and use and care, visit nomex.com/fabrics

 **DuPont Personal Protection**
 **@DuPontPPE**

All fabrics in our portfolio are suitable to be used for arc flash protection as per NEC, NESC, NFPA 70E and OSHA requirements.

Product safety information is available upon request. All data are from certification tests. Data can vary among testing labs.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentations. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DUPONT MAKES NO WARRANTIES AND ASSUMES NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ® or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2019 DuPont. MT-1040-US (09/19)